

Amendments to the Claims

This listing of claims will replace all prior versions and listings of claims in the subject application.

Listing of Claims:

What is claimed is:

1. (Withdrawn) A metallic alloy for coating a metal surface comprising a deoxidizing element, wherein said deoxidizing element reduces a metal-oxide layer on said metal surface.
2. (Withdrawn) The metallic alloy of claim 1, wherein said deoxidizing element is a transition metal, selected from the group consisting of manganese, chromium, vanadium, titanium, zirconium, hafnium, niobium, tantalum, aluminum, lanthanide metals in combination with and oxygen seeking nonmetal/metalloid selected from the group consisting of silicon, carbon, boron, phosphorous, sulfur and combinations thereof.
3. (Withdrawn) The metallic alloy of claim 1 wherein said deoxidizing element is further characterized in that it does not chemically interact with said metallic alloy.
4. (Withdrawn) The metallic alloy of claim 1, wherein said metallic alloy base metal is selected from the group consisting of iron, nickel, cobalt, manganese, chromium, titanium, vanadium, zirconium, niobium, hafnium, tantalum, tungsten, and aluminum.
5. (Withdrawn) The metallic alloy of claim 1 wherein said deoxidizing element is present at a level of 5 to 70%.
6. (Currently Amended) A method of forming a metallic coating on an oxidized metal surface layer comprising:
providing an atomized iron based metallic coating alloy wherein said alloy includes deoxidizing elements including manganese, and a metal selected from the group consisting of

chromium, vanadium, titanium, zirconium, hafnium, niobium, lanthanide metals and combinations thereof and an oxygen seeking nonmetal/metalloid including boron, wherein said deoxidizing element is present between 5%-70% in said iron based metallic coating alloy; and

forming a metallic coating at a thickness of 40 mil to 110 mil by high velocity oxy-fuel spray by melting said iron based metallic coating alloy to a liquid state;

applying said liquid melt of said iron based metallic coating alloy to said oxidized metal surface and removing said oxidized metal surface layer with said liquid melt of said iron based metallic coating alloy to provide a metal surface that is relatively clean of said oxidized metal surface layer—and susceptible to receipt of a metallic coating and wherein said deoxidizing elements remove oxygen from the metal surface layer and said deoxidizing elements are present in said alloy melt such that said deoxidizing elements remain dissolved in said alloy melt to retain an affinity for oxygen; and

applying an iron based metallic coating alloy to said metal surface that is relatively clean of said oxidized metal surface layer wherein said iron based metallic coating has an ASTM C633 bond strength of at least about 12,000 psi and said bond strength is present at [[a]]said coating thickness from 40 mil to 110 mil and wherein failure of said coating does not occur at a coating/metal surface interface.

7. (Previously Presented) The method of claim 6 wherein said step of melting said iron based alloy to a liquid state comprises forming a liquid state with no precipitates of said deoxidizing elements existing in said liquid state.

8. (Cancelled)

9. (Cancelled)

10. (Cancelled)

11. (Cancelled)

AMENDMENT

Serial Number: 10/776,472

Filing Date: February 11, 2004

Title: Highly Active Liquid Melts Used to Form Coatings

Page 4

Docket: NANO004U

12. (Previously Presented) The method of claim 6 wherein said oxygen seeking non-metal/metalloid is selected from the group consisting of silicon, carbon, phosphorus, sulfur and combinations thereof.

13. (Previously Presented) The method of claim 6 wherein said manganese is present at about 2.3 %.

14. (Previously Presented) The method of claim 6 wherein said manganese is present at about 0.8 %.

15. (Cancelled)

16. (Cancelled)